

GRAFTech International

SL™ Graphite

GrafTech International is a global leader in graphite and carbon products. We enable customer leadership better and faster than our competition, through the creation, innovation and manufacture of carbon and graphite material science based solutions.

Grade SL™ Graphite

Densified prior to graphitization, SL™ graphite is for applications requiring higher densities and good mechanical strength.

Typical Applications

- CZ silicon crystal growth
- Quartz
- Casting molds and furnace parts for hot metal

Sizes

20" & 22" diameter rounds
 500 mm & 550 mm diameter rounds
 20" and 22" cross-section rounds
 500 and 550 mm cross-section rounds
**Other sizes available on request*

Typical Properties at Room Temperature

	<u>ENGLISH</u>	<u>WG</u>	<u>AG</u>	<u>METRIC</u>	<u>WG</u>	<u>AG</u>	<u>SI</u>	<u>WG</u>	<u>AG</u>
Density	lbs/ft ³	110		g/cm ³	1.76		g/cm ³	1.76	
Maximum Particle Size	Inches	0.030		mm	0.76		mm	0.76	
Specific Resistance	10 ⁻⁴ Ω in.	2.9	3.4	μΩm	7.4	8.5	μΩm	7.4	8.5
Flexural Strength	psi	2900	2465	kg/cm ²	204	173	MPa	20	17
Young's Modulus	10 ⁶ psi	1.45	1.23	kg/mm ²	1019	866	GPa	10.0	8.5
Tensile Strength	psi	2030	1740	kg/cm ²	143	122	MPa	14	12
Compressive Strength	psi	8000	8000	kg/cm ²	562	562	MPa	55	55
Permeability	Darcy	0.02	0.02	Darcy	0.02	0.02	Darcy	0.02	0.02
Hardness	Rockwell "R"	93		Rockwell "R"	93		Rockwell "R"	93	
C.T.E. (to 100 °C)	10 ⁻⁶ /°F	1.8	2.1	10 ⁻⁶ /°K	3.2	3.8	10 ⁻⁶ /°K	3.2	3.8
Thermal Conductivity	BTU-ft/hr ft ² °F	90	81	W/mK	156	140	W/mK	156	140
Ash Content	ppm	1500		ppm	1500		ppm	1500	

This information is based on data believed to be reliable but GrafTech makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. GrafTech's liability to purchasers is expressly limited to the terms and conditions of sale. SL is a trademark of GrafTech International Holdings Inc.

GT-5030
Rev. 2

101 N. Philippe Pike, Clarksburg, WV 26323-0120
Ph: +1-800-842-8805; +1-304-624-1253

La Lechere, 73264 Aigueblanche Cedex, France
Ph: +33 04 79 41 45 00

Via Forno Allione, 2, I-25040 Malonno, Brescia, Italy
Ph: +39 03 64 63 01 31

© 2009 GrafTech International Holdings Inc.

GRAFTech
International

www.graftech.com